

Cleveland State University EngagedScholarship@CSU

Undergraduate Research Posters 2016

Undergraduate Research Posters

2016

Elimination of Acoustical Noise for STM Examination of Pentacene Crystallization on Si (001)

William Myers
Cleveland State University

Mark Bowling
Cleveland State University

Follow this and additional works at: https://engagedscholarship.csuohio.edu/u_poster_2016

How does access to this work benefit you? Let us know!

Recommended Citation

Myers, William and Bowling, Mark, "Elimination of Acoustical Noise for STM Examination of Pentacene Crystallization on Si (001)" (2016). *Undergraduate Research Posters 2016*. 25.
https://engagedscholarship.csuohio.edu/u_poster_2016/25

This Book is brought to you for free and open access by the Undergraduate Research Posters at EngagedScholarship@CSU. It has been accepted for inclusion in Undergraduate Research Posters 2016 by an authorized administrator of EngagedScholarship@CSU. For more information, please contact library.es@csuohio.edu.



This digital edition was prepared by MSL Academic Endeavors, the imprint of the Michael Schwartz Library at Cleveland State University.

Elimination of Acoustical Noise for STM Examination of Pentacene Crystallization on Si (001)

College of Sciences and Health Professions

Student Researchers: William Myers and Mark Bowling

Faculty Advisor: Jessica E. Bickel

Abstract

Organic electronics are used in traditional solar cells and also in flexible electronics. Unfortunately, the conductivities of organic semiconductors are significantly lower than their inorganic counterparts. This project examines crystallization by directed self-assembly of the organic molecules via a surface reconstruction as a method to increase conductivity. The crystallization is characterized by Scanning Tunneling Microscopy (STM). In order to achieve optimal STM images, this work examined: (1) noise isolation, (2) etching sharp STM tips and (3) achieving reconstructed Si surface. The STM is housed in a glovebox to keep the surface reconstructions and organic molecules from degrading. However, acoustical noise of the glovebox circulation pump makes achieving atomic resolution impossible. Introducing a foam-lined acoustical shell around the microscope significantly reduced acoustic noise and atomic resolution is achieved. We also determined optimal PtIr tip etching procedures, demonstrating that an alternating current of 40V in a 1M CaCl₂ solution results in a tip with an $\sim 13\mu\text{m}$ radius of curvature, comparable to other PtIr tips found in literature. Finally, we demonstrated a Si(001) surface with 20nm terrace widths and two atomic height steps achieved by cleaving inside the N₂ environment.